



TECHNICAL DATA SHEET #4

PDC® F-851's' IMC eccs®

WATER BASED ACRYLIC In Mold Coating
FOR INDUSTRIAL USE ONLY

DESCRIPTION:

F-851's' is a water base in mold barrier coating is specifically developed to use as an IMC [in mold coating] for flexible polyurethane foams. F-851's' is very economical, efficient, non-flammable and also reduces the risk of coating adhesion issues with top coats. F-851's' is used in manufacturing of patient positioning products such as wheelchair cushions, positioning aids as well as other industrial applications.

OTHER FEATURES INCLUDE:

Intended for use in molds with starting temps 80-110 °F.

Water base clean up.

One component-no catalyst

Custom color matching

SPECIFICATIONS:

Solids: (wt.) 36%

Shore A Hardness 12

Shelf life: 1+ years at 77°F unopened container

Coverage: 250 sq ft/ gallon @ 2 mils.

Finish: matte

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the applications of this information or the safety and suitability of our products, either alone or in combination with other product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products whether used alone or in combination with other products. Ever changing V.O.C. regulations in your area may require you to contact local authorities for proper use and/or disposal of this product. Should you need further assistance, please contact PLASTI DIP INTERNATIONAL technical service.

PDC and eccs are registered trademarks of PLASTI DIP INTERNATIONAL
Performix and logo are trademarks of PLASTI DIP INTERNATIONAL
BINKS is a registered trademark of BINKS MFG. CO., Franklin Park, IL

**SURFACE PREPARATIONS:
MIX WELL BEFORE USE.**

All surfaces to be coated must be free of any oils, dust, release agent build up or loose foam particles. .
Allow any solvent to flash before applying F-851's'.

USE ADEQUATE VENTILATION.

SPRAYING: GENTLY MIX BEFORE SPRAYING.

Pressure pot sprayers are recommended. Apply light [damp] overlapping coat of F-851's' to mold, holding gun 6"-12" from surface, using 4"-6" pattern. Be sure to coat the entire surface. Allow F-851's' to become "tacky" before pouring polyurethane chemicals. Allow adequate "cycle time" before removing finished product.

Contact OEM Technical Support for more details regarding your specific application and process and top coat recommendations.

RECOMMENDED EQUIPMENT AND SETTINGS:

Binks® model 2100 gun	Material: 20psi
Nozzle: 63C	Atomization: 10-30psi
Cap: 63PB or 66SD	Dilution: not recommended
Needle: 363A	Clean up: water, MEK once dried.