



TECHNICAL DATA SHEET #48

PDC® F-884 IMC

VINYL BASED- IN MOLD FOAM COATING
FOR INDUSTRIAL USE ONLY

DESCRIPTION:

F-884 is a unique high performance vinyl IMC [in mold coating] that is spray applied into the mold tool to provide a durable, flexible, chemical and UV resistant coating on flexible urethane molded products.

F-884 acts as the finish coat or can be used as an in mold barrier coat and post coated after trimming. F-884 offers excellent durability, flexibility, abrasion, UV and chemical resistance. The demand for a high performance vinyl based **IMC** [in mold coating] makes this innovative product the new alternative for your specialty foam products applications in the medical, sporting goods, pool and spa, leisure, automotive and industrial markets.

OTHER FEATURES INCLUDE:

Intended for use in molds with starting temps 120-135° F

Super fast dry time

Custom color matching

Unbeatable chlorine, bromine and other harsh chemical resistance.

SPECIFICATIONS:

Solids: (wt.) F-884 10%

Shelf life: 1+ years at 77°F unopened container

Finish: semi gloss

Coverage: 225 sq ft/ gal @ 1 mil

ALTERNATIVE PRODUCTS:

F-887, F-897, F-899

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the applications of this information or the safety and suitability of our products, either alone or in combination with other product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products whether used alone or in combination with other products. Ever changing V.O.C. regulations in your area may require you to contact local authorities for proper use and/or disposal of this product. Should you need further assistance, please contact PLASTI DIP INTERNATIONAL technical service.

SURFACE PREPARATIONS:**MIX WELL BEFORE USE.**

All surfaces to be coated must be free of any oils, dust or loose foam particles. Allow solvent to flash before applying F-884 to mold.

USE ADEQUATE VENTILATION.**MIXING:**

F-884 may coagulate during storage, requiring thorough high speed sheering mixing before use each day. For best results, a high speed air or explosion proof electric drum mixer along with a 7" Cowles® blade (or similar dispersion blade) provides best results. For 5 gallon pail mixers use 3" Cowles® blade. Sheer F-884 before use each day, gentle remix throughout the day is recommended to ensure color consistency.

SPRAYING: Siphon Gun/ Pressure pot sprayers may be used. F-884 as an **IMC** [in mold coating]. Apply wet, overlapping coats to mold holding gun 6"-12" from surface, using 4"-6" pattern. Be sure to coat entire surface evenly. Allow to dry to the touch before adding polyurethane chemicals. Allow adequate "bake" time for the foam before removing finished product. If a seam is present after removal of any flashing, either touch up with paint brush or proceed to finish coat step.

F-884 as a finish coat. Apply wet, overlapping coats, holding gun 6"-12" from surface, using 4"-6" pattern. Allow to dry to the touch before applying additional coats or turning part over. Its recommended that 2-3 coats be applied for best results. Allow coated part to dry 4 to 6 hours minimum [depending on mil thickness applied] before handling and 24 hours minimum before packaging or shipping.

RECOMMENDED EQUIPMENT AND SETTINGS:

Binks® model 2100 gun	Material: 20psi
Nozzle: 63B	Atomization: 10-25psi
Cap: 63PB	Dilution: up to 10% toluene
Needle: 363A	Clean up: toluene

HINTS:

Always use proper ventilation and protection. Allow overnight drying whenever possible. Avoid excessive air movement, heat or humidity. To accelerate drying of coated parts: air dry coated part 10-15 minutes then force dry 30-60 minutes at 90-120° F being careful not to distort or damage foam substrate. Contact foam manufacturer for guidelines.

Caution:

Flexible molded polyurethane foam may have a tendency to out gass which can cause delamination or blistering of the coating or distortion of the part. Use caution when speed drying or shipping coated parts by air freight or into hot conditions too soon after completing part.